

## RHP235 HIGH TACK 90% PCP RPET HOT MELT PACKAGING TAPE

### TYPICAL APPLICATIONS

- For manual and automated industrial sealing of medium-weight, highly recycled cartons, particularly 100 percent recycled

### PRODUCT FEATURES

- 90% Post-Consumer Recycled 23 micron rPET film
- Recycled™ Series medium duty packaging tape for use on highly recycled or 100% PCW/OCC cartons
- Higher shear, tack and adhesion on recycled corrugate, recycled paper and a variety of other substrates
- High-tack synthetic rubber/resin hot melt adhesive featuring Hold Strong® technology for a long-lasting, secure seal
- Special release coating for Good to the Core® performance and consistent, low force unwind off the roll
- Performs reliably to the core for efficient tape consumption

### CONSTRUCTION

Backing: 23 micron 90% Post-Consumer Recycled rPET film

Adhesive: Synthetic rubber/resin hot melt adhesive

### STANDARD WIDTHS

1.88 in; 2.08 in; 2.83 in  
48 mm; 53 mm; 72 mm

### STANDARD LENGTHS

109.3 yd, 1640 yd

100 m, 1500 m

Lead times may apply. Please contact Shurtape customer service for information related to stock and non-stock sizes and colors.

### STANDARD CORE SIZE

3 in

### APPLICABLE STANDARDS

ASTM D 1974/D 1974M-16

CID A-A-1684C

FDA Indirect Contact CFR 21, 175.105

### STORAGE & USAGE CONDITIONS

Tape should be stored in its original packaging in a cool, dry area away from direct sunlight and should be used within 12 months of date of shipment.

Surfaces to which tape is applied should be clean, dry and free of grease, oil or other contaminants.

### COLOR



### PHYSICAL PROPERTIES

Adhesion to Backing - Machine Rolls  
CZXd

Adhesion to Stainless Steel

Application Temperature Range

Elongation

Holding Power to Fiberboard

MD Tensile Strength

Service Temperature Range

Tensile

Tensile Strength - Longitudinal Direction

Thickness

### STANDARD METRIC

10 oz/in width 1.09 N/10 mm

63 oz/in width 6.90 N/10 mm

35 F to 110 F 2 C to 43 C

135% 135%

15,000 minutes 15,000 minutes

23 lbs/in 40.3 N/10 mm

-20 F to 150 F -29 C to 66 C

23 lbs/in 40.3 N/10 mm

23 lbs/in width 40.3 N/10 mm

1.75 mils 0.04 mm

Physical and performance characteristics shown above are obtained from tests recommended by PSTC, ASTM, government agencies or Shurtape Technologies, LLC, Quality Assurance and Technical Service departments and do not represent a guarantee of product performance. Individual rolls may vary slightly from these averages. The user should determine whether the product is fit for a particular purpose and is suitable for the user's method of application before use.



\*To Learn more visit [www.LINCsystems.com](http://www.LINCsystems.com)